

TABLA Nº19

Institutions with the best			80-100
Table 6.6. Suggested Layer Coefficients for Rating of Permanent Layer Interest			
ACTIVIDAD	REFERENCE COEFFICIENT	COEFFICIENT	
At Surface	Little or no alligator cracking and/or only low-severity	0.95 to 0.98	
	slab-edge cracking		
	< 10 percent low-severity alligator cracking and/or	0.90 to 0.95	
	< 5 percent medium- and high-severity transverse cracking		
	> 10 percent low-severity alligator cracking and/or	0.85 to 0.90	
	> 10 percent medium-severity alligator cracking and/or		
	> 5-10 percent medium- and high-severity transverse cracking		
	> 10 percent medium-severity alligator cracking and/or	0.80 to 0.85	
	< 10 percent high-severity alligator cracking and/or		
	> 10 percent medium- and high-severity transverse cracking		
Half-thick Slab	< 10 percent high-severity alligator cracking and/or	0.68 to 0.75	
	> 10 percent high-severity transverse cracking		
	Little or no alligator cracking and/or only low-severity	0.80 to 0.85	
	transverse cracking		
	< 10 percent low-severity alligator cracking and/or	0.75 to 0.80	
	< 5 percent medium- and high-severity transverse cracking		
	> 10 percent low-severity alligator cracking and/or	0.70 to 0.75	
	< 10 percent medium-severity alligator cracking and/or		
	< 5-10 percent medium- and high-severity transverse cracking		
	> 10 percent medium-severity alligator cracking and/or	0.65 to 0.70	
Greater than or Subbase	< 10 percent high-severity alligator cracking and/or	0.50 to 0.55	
	> 10 percent high-severity transverse cracking		
	No evidence of potholes, degradation, or contamination by flow	0.45 to 0.50	
	Some evidence of potholes, degradation, or contamination by flow	0.35 to 0.45	